

CHEMICAL RESISTANCE CHART OF SUPERCONCRETE TREATED WITH BETON HARDNER

	Finishing by BETON SKUDO	Finishing by BETON SKUDO and BETON GUARD LITHIUM
Aluminum Chlorid e	NE	NE
Ammonium Chloride	NE	NE
Anti Freeze	NE	NE
Aviation Gasolines	M	NE
Battery Acid 30% Sulfuric Acid	S	SS
Brake Fluid	M	SS
Carbonic Acid 85%	NE	NE
Chromic Acid 10%	NE	NE
Cooking Oil	M	NE
Ethyl Alcohol (Beer)	NE	NE
Gasoline	NE	NE
Grease	M	NE
HCL (10%)	S	SS
Iodine	S	NE
Isopropyl Alcohol	NE	NE
Jet Fuel	M	NE
Ketchup	NE	NE
Lemon Juice – Citric Acid	M	NE
Milk	NE	NE
Motor Oil	M	NE
Mustard	NE	NE
NAOH (10%)	NE	NE
Orange Juice – Citric Acid	M	NE
Phosphoric Acid 85%	SS	NE
Potassium Dichromate	M	NE
Red Wine	NE	NE
Household Bleach	NE	NE
Sodium Sulfate	NE	NE

Sodium Sulfit	NE	NE
Tannic Acid	M	NE
Transmission Fluid	M	NE
Urine	M	NE
Vinegar Acetic Acid (10%)	M	NE
Zinc Sulfate	M	NE

- * S = Stain
- * NE = No effect
- * SS = Slight stain
- * M = Minimal

The resistance is based on treated concrete upon proper application by Using Beton Hardner , Beton Skudo and BETON GUARD LITHIUM .